

# Technical Data

## Jotacote Universal



### Product description

Jotacote Universal is a two-pack, abrasion resistant, high solids polyamine cured pure epoxy based primer/finish coat which may be applied in high film thickness.

---

### Recommended use

A universal primer specifically designed for use in newbuilding situations. To be used on steel alone or in combination with various systems. If a cosmetic finish is required, it should be used together with a topcoat. Gives excellent corrosion protection both in salt and fresh water. Jotacote Universal Aluminium Lumi is intended as first coat in water ballast tanks and utilises luminous pigments to aid application and inspection.

For application in water ballast tanks at newbuilding stage in accordance with PSPC (IMO Res. MSC 82/W), see the "Application procedure for water ballast tanks - Jotacote Universal".

---

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry ( $\mu\text{m}$ )	75	300	160
Film thickness, wet ( $\mu\text{m}$ )	105	415	220
Theoretical spreading rate ( $\text{m}^2/\text{l}$ )	9,6	2,4	4,5

### Comments

For DFTs below 150  $\mu\text{m}$  thinner should be used.

---

### Approvals

B1 classification by Det Norske Veritas (DNV) for water ballast tanks.

---

## Physical properties

<b>Colour</b>	Aluminium and aluminium red toned, Aluminium Lumi, Buff, Grey, Red
<b>Solids (vol %)*</b>	72 ± 2
<b>Flash point</b>	35°C ± 2 (Setaflash)
<b>VOC</b>	2,17 lbs/gal (260 gms/ltr) USA-EPA Method 24 240 gms/ltr UK-PG6/23(97). Appendix 3
<b>Gloss</b>	Semigloss
<b>Gloss retention</b>	Fair
<b>Water resistance</b>	Excellent
<b>Abrasion resistance</b>	Very good
<b>Solvent resistance</b>	Excellent
<b>Chemical resistance</b>	Excellent
<b>Flexibility</b>	Good
<b>Compatibility with cathodic protection</b>	Very good

\*Measured according to ISO 3233:1998 (E)

Hong Kong rules: Category of paints - Other vessel coatings; VOC 260 gms/ltr HK EPD method (Ready to use); Exempt compound - N/A; Specific gravity: 1.33 kg/ltr (A+B); Both VOC and Specific gravity values provided are typical values, subject to changes when different colour involved.

---

## Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

### Bare steel

Cleanliness: Blast-cleaning to Sa 2½ (ISO-8501-1:2007). Power tool cleaning to min. St 2 (ISO 8501-1:2007) may be acceptable, subject to exposure conditions.

### Shopprimed steel

Clean, dry and undamaged approved shopprimer.

### Coated surfaces

Clean, dry and undamaged compatible primer. Please contact your local Jotun office for more information.

### Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

## Condition during application

The coating could be applied down to -15°C surface temperature. Temperature of the substrate should be minimum 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure proper drying and curing. Do not use heated air until the solvents have evaporated from the paint film to avoid surface drying and solvent entrapment. The coating should not be exposed to oil, chemicals or mechanical stress until cured. During application and the initial drying of the coating, the coating should not be exposed to high humidity as this can result in loss of gloss.

---

## Application methods

<b>Spray</b>	Use airless spray
<b>Brush</b>	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
<b>Roller</b>	May be used for small areas but not recommended for first primer coat, however when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

---

## Application data

<b>Mixing ratio (volume)</b>	3:1
<b>Mixing</b>	3 parts Comp. A (base) to be mixed thoroughly with 1 part Jotacote Universal, Comp. B (curing agent).
<b>Induction time</b>	10 minutes.
<b>Pot life (23°C)</b>	1½ hours (reduced at higher temperatures)
<b>Thinner/Cleaner</b>	Jotun Thinner No. 17
<b>Guiding data airless spray</b>	
<b>Pressure at nozzle</b>	15 MPa (150 kp/cm², 2100 psi)
<b>Nozzle tip</b>	0.43-0.79 mm (0.017-0.031")
<b>Spray angle</b>	40-80°
<b>Filter</b>	Check to ensure that filters are clean.

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

<b>Substrate temperature</b>	<b>-10°C</b>	<b>0°C</b>	<b>10°C</b>	<b>23°C</b>	<b>40°C</b>
<b>Surface dry</b>	36 h	14 h	5 h	2,5 h	1 h
<b>Through dry <sup>1</sup></b>	4 d	30 h	10 h	5 h	2 h
<b>Cured</b>		21 d	10 d	7 d	3 d
<b>Dry to recoat, minimum <sup>2</sup></b>	42 h	18 h	7 h	4 h	2 h
<b>Dry to recoat, maximum <sup>3</sup></b>					
<b>Substrate temperature</b>	<b>-5°C</b>	<b>5°C</b>			
<b>Surface dry</b>	20 h	8 h			
<b>Through dry <sup>1</sup></b>	48 h	16 h			
<b>Cured</b>		14 d			
<b>Dry to recoat, minimum <sup>2</sup></b>	24 h	10 h			
<b>Dry to recoat, maximum <sup>3</sup></b>					

1. The earliest time that it is possible to exert mechanical strain on the coating, i.e. walk on to recoat.

2. The earliest time for recoating with the same generic type of paint. Note that the paint film is not hard at this time and can not withstand mechanical strain.
3. Provided the surface is free from chalking and other contamination prior to application, there is normally no overcoating time limit. Best intercoat adhesion occurs, however, when the subsequent coat is applied before preceding coat has cured. If the coating has been exposed to direct sunlight for some time, special attention must be paid to surface cleaning and mattening/removal of the surface layer in order to obtain good adhesion

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

Above water

<b>Jotacote Universal</b>	<b>2 x 125 µm</b>	<b>(Dry Film Thickness)</b>
Hardtop AS/XP	1 x 50 µm	(Dry Film Thickness)

For water ballast tanks

<b>Jotacote Universal</b>	<b>2 x 160 µm</b>	<b>(Dry Film Thickness)</b>
---------------------------	-------------------	-----------------------------

Other systems may be specified, depending on area of use

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use.

---

## Packing size

20 litre unit: 15 litres Jotacote Universal Comp. A in a 20 litre container and 5 litres Jotacote Universal, Comp. B in a 5 litre container.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

---

## DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice. Minor product variations may be implemented in order to comply with local requirements.

If there is any inconsistency in the text the English (UK) version will prevail.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 26 NOVEMBER 2010 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED